

Red Oxide Primer is a genuine red oxide paint for ferrous metals  
It also acts as a good holding primer prior to finishing interior and exterior metalwork  
Colour Range - Red Oxide  
Packaging - 1, 2.5, 5, 20, 205, & 1000 litres

#### PROPERTIES

Drying Time - Under normal drying conditions surface dry 4-6 hours and recoatable after 16 hours.  
Allow for adequate ventilation during the drying period

Finish - Eggshell

Composition Pigment: Iron oxide and extenders

Resin: Alkyd

Solvent: Dearomatised White Spirit

Spreading Rate - Up to 12m<sup>2</sup> per litre on smooth surfaces

Wet Film Thickness

67 micrometres at 12m<sup>2</sup> per litre

Dry Film Thickness

35 micrometres at 12m<sup>2</sup> per litre

Volume Solids

53%

Flash Point - 40°C

VOC Content - EU limit value for this product (cat.A/i): 500 g/l (2010)

This product contains max. 399 g/l VOC Limitations

Do not apply when air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

#### PREPARATION

##### New Surfaces

Surfaces must be clean and free from anything that will interfere with the materials to be applied. Wash with hot water and liquid detergent solution to remove oil, grease or any other contaminants, frequently changing the water. Rinse thoroughly with clean water. Allow to dry. Remove all millscale and rust back to clean metal. Remove all residues. Prime within the working day with one coat of Red Oxide Primer.

##### Previously decorated soiled surfaces

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect paint. Feather edges of sound paint. Remove all dust. Remove all rust. Spot prime bare areas with one coat of Red Oxide Primer. Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Wet abrade to provide a key. Rinse with clean water to remove all residues. Allow to dry. Bring forward spot primed areas with one coat of Red Oxide Primer.

#### COATING SYSTEM

Apply one or two coats as required.

#### APPLICATION

Stir well before use. Apply by brush or roller

#### CLEANING

Return surplus material to container. Clean with a proprietary cleaner immediately.

#### MAINTENANCE

Between maintenance redecoration surfaces may be washed with a warm water and liquid detergent

#### INFORMATION FOR CDM FILE

solution to remove surface dirt.

#### HEALTH AND SAFETY

Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other products are freely available from the place of purchase or the address below. Store in secure dry conditions between 5°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks

#### GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened